

### **Amendments to the Claims:**

This listing of claims will replace all prior versions and listings of claims in the application.

### **Listing of Claims:**

1. (ORIGINAL) A method of manufacturing a semiconductor device in patterning of a conductive film and a thin dielectric film, comprising the steps of:  
  
a first etching step of carrying out anisotropic etching until most of the conductive film in a flat portion disappears; and  
  
a second etching step of increasing a selective ratio to the dielectric film to etch the conductive film in an unnecessary portion in a state in which the conductive film is caused to remain such that a thickness of the dielectric film provided under the grain boundary can be held to prevent oxidation species from reaching an interface with a substrate after the first etching step.
2. (ORIGINAL) The method of manufacturing a semiconductor device according to claim 1, wherein the second etching step includes a step of carrying out etching while growing a silicon oxide film by a reaction of the oxidation species and the substrate.
3. (CURRENTLY AMENDED) The method of manufacturing a semiconductor device according to claim 1 ~~or~~ 2, wherein the second etching step is executed in such a gas atmosphere that a concentration of the oxidation species is higher than that in the first etching step.
4. (CURRENTLY AMENDED) The method of manufacturing a semiconductor device according to claim 1 ~~or~~ 2, wherein the second etching step is executed at an in-chamber pressure of 2 mTorr or less.

5. (ORIGINAL) The method of manufacturing a semiconductor device according to claim 1, wherein the dielectric film is a silicon oxide film having a thickness of 5 nm or less.

6. (CURRENTLY AMENDED) The method of manufacturing a semiconductor device according to claim 1 ~~or~~ 2, wherein the conductive film is a silicon type conductive film.

7. (ORIGINAL) The method of manufacturing a semiconductor device according to claim 6, wherein the silicon type conductive film is a polycrystalline silicon film.

8. (CURRENTLY AMENDED) The method of manufacturing a semiconductor device according to ~~any of claim~~[[s]] 1 ~~to~~ 7, wherein the first and second etching steps are ECR plasma etching steps.

9. (ORIGINAL) The method of manufacturing a semiconductor device according to claim 6, wherein the second etching step uses a hydrogen bromide (HBr)/Cl<sub>2</sub>/O<sub>2</sub> plasma.

10. (ORIGINAL) The method of manufacturing a semiconductor device according to claim 9, wherein the first etching step uses the hydrogen bromide (HBr)/Cl<sub>2</sub>/O<sub>2</sub> plasma, and a concentration of oxygen in the second etching step is higher than that of oxygen in the first etching step.

11. (ORIGINAL) The method of manufacturing a semiconductor device according to claim 9, wherein the first etching step uses a Cl<sub>2</sub>/O<sub>2</sub> plasma.

12. (CURRENTLY AMENDED) The method of manufacturing a semiconductor device according to claim 1 ~~or~~ 2, wherein the dielectric film is a gate oxide film and the conductive film is a gate electrode.